

Avery® 5500 Cast Translucent

Features

- Outstanding colour fastness, durability and outdoor performance
- Excellent colour uniformity in reflected and transmitted light
- Compatible with a wide range of rigid and flexible substrates
- Dimensionally stable backing for easy converting
- Excellent conversion properties on computerised cutters
- Easy cutting and weeding
- Excellent dimensional stability
- Excellent UV, temperature, humidity and salt-spray resistance
- Batch reference and product identification printed on liner for traceability

Conversion

- | | |
|--|--|
| <input checked="" type="checkbox"/> Flat bed cutters | <input type="checkbox"/> Cold overlaminating |
| <input checked="" type="checkbox"/> Friction fed cutters | <input type="checkbox"/> Estat printing |
| <input checked="" type="checkbox"/> Die cutting | <input type="checkbox"/> Water based inkjet |
| <input checked="" type="checkbox"/> Thermal transfer | <input type="checkbox"/> Solvent inkjet |
| <input checked="" type="checkbox"/> Screen printing | <input type="checkbox"/> UV Cured inkjet |

Custom Colours

A fast colour matching service is offered for projects where specific colours are required. A minimum order quantity of only 61m² is required.

Uses

Avery 5500 Cast Translucent is designed for use in a wide range of internally illuminated signs and canopies (rigid and flexible) or as a creative addition to window graphics.

Description



Film: 50 micron cast vinyl



Adhesive: Permanent acrylic



Backing: One side coated bleached Kraft paper, 140gsm



Outdoor life:
up to 10 years- Middle Europe
up to 7 years- Asia Pacific



Colours: 85 standard

Common Applications

- Internally illuminated signs
- Architectural signage
- Window graphics

Physical characteristics

General

Caliper, facefilm	ISO 534	50 micron
Caliper, facefilm & adhesive	ISO 534	80 micron
Dimensional stability	DIN 30646	0.2 mm max.
Tensile strength	DIN 53455	22 N/mm ²
Elongation	DIN 53455	75%
Gloss	ISO 2813, 20 ^º	25 %
Adhesion, initial	FINAT FTM-1	70% of ultimate values
Adhesion, ultimate	FINAT FTM-1 PMMA	720 N/m
	Glass	640 N/m
	Stainless Steel	720 N/m
Flammability		Self extinguishing
Shelf life	Stored at 22 °C/50-55 % RH	2 years
Accelerated aging	DIN 53387 1500 hours exposure	No significant colour change
Durability **	Vertical exposure	
	Black & white	Up to 7 years
	Colours	up to 7 years
	Vac-formed	up to 5 years

Thermal

Application temperature		Minimum: + 10°C
Heat resistance	3 weeks exposure at 80 °C	No significant colour change

Important

Information on physical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of any material for their specific use.

All technical data is subject to change without prior notice.

Warranty

Avery® materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give guarantee, warranty, or make any representation contrary to the foregoing.

All Avery® materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

**Durability

Durability is based on exposure conditions in the Asia Pacific region. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing north in the southern hemisphere or south in the northern hemisphere; in areas of long high temperature exposure such as northern Australia; in industrially polluted areas or high altitudes, exterior performance will be decreased.

***Information unavailable at time of printing.

Test Methods

Dimensional stability:

Is measured on a 150 x 150 mm aluminium panel to which a specimen has been applied; 72 hours after application the panel is exposed for 48 hours to + 70 °C, after which the shrinkage is measured.

Adhesion:

(FTM-1, FINAT) is measured by peeling a specimen at a 180° angle from a stainless steel or float glass panel, 24 hours after the specimen has been applied under standardised conditions. Initial adhesion is measured 20 minutes after application of the specimen.

Flammability:

A specimen applied to aluminium is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the flame.

Temperature range:

A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. 1 hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

Chemical Resistance:

All chemical tests are conducted with test panels to which a specimen has been applied. 72 hours after application the panels are immersed in the test fluid for the given test period. 1 hour after removing the panel from the fluid, the specimen is examined for any deterioration.

Corrosion Resistance:

A specimen applied to aluminium is exposed to saline mist (5% salt) at 35°C. After exposure, the film is removed and the panel is examined for traces of corrosion.