

# MetaGuard 'FloorArt'

DécorMark Textured Floor Overlamine



## Product Description

MetaGuard FloorArt is a textured floor overlamine offering Décor and promotional branding opportunities for short term indoor use. The 100 micron matt embossed film gives a durable protection to graphics, with easy to clean finish. This versatile product can also be applied to wall graphics, for a one product solution. MetaGuard FloorArt has an anti-slip finish tested to DIN 51130:2014, achieving an R9 rating. The recommended matched media is Metamark MDPH or MDPHB. Suitable with Solvent, Eco Solvent, UV and Latex prints.

## Features and Benefits

- Matched to Metamark MDPH or MDPHB.
- 100 micron textured film.
- R9 slip rated
- BS 7976 certified
- Textured anti-scuff finish.
- SandTex lustre film minimalises glare.

Face Film		Finishes		
Face Film	Monomeric Calendered PVC	Finishes Available	MG-F	FloorArt
Gauge (ISO 2286-3)	100 micron nominal	<b>Roll Presentation</b>		
Tensile strength	65N/25mm MD / 57N/25mm TD norm	Roll Widths	0.76 / 1.37m / 1.52m	
<b>Adhesive</b>		Roll Lengths	10m / 50m	
Type	Permanent Solvent-Free Acrylic	<b>Durability</b>		
Adhesion to glass 20 mins	14N/25mm nominal	Shelf Life	1 years. (10-20°C and 50% R.H).	
Adhesion to glass 24 hour	18N/25mm nominal	Durability	1 year floor application 3 years wall application	
Application temperature	+10°C to +40°C	Fire Rating	Self-extinguishing.	
Service temperature	-30°C to +100°C	Slip Certification	BS 7976-2:2002 cert (Slider 96) DIN 51130:2014 – Category R9	
<b>Release Liner</b>		Chemical Resistance	Unprinted film resistant to mild acids, aliphatic solvents, salt and alkali, diesel, gasoline, paraffin, hydraulic oil, antifreeze.	
Print	'Metamark Digital Vinyl' grey print			
Weight	140 gsm nominal			
Type	Layflat kraft with PE coating			

## Handling and Application

- This product is suitable for cold lamination using a laminator.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film, ensure free from dust and static.
- Allow the inks to cure before overlaminating, this is usually 24-48 hours.
- Suitable for use on solvent, eco-solvent, UV and latex prints.
- Apply around 30°C on the top roller to prevent silvering of the adhesive.
- Refer to [www.metamark.co.uk](http://www.metamark.co.uk) for further application guidelines.
- The user should determine suitability of the overlamine to the print media.

## MetaSure® Warranty

Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Media and Overlaminates will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark Media and Overlaminates becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

## Metamark (UK) Limited

- Lunsdale • New Quay Road • Lancaster • LA1 5QP • Tel +44 (0)1524 387140
- Metamark House • Genesis Business Park • Albert Drive • Woking • GU21 5RW • Tel +44 (0)1483 571111

[sales@metamark.co.uk](mailto:sales@metamark.co.uk)  
[www.metamark.co.uk](http://www.metamark.co.uk)