# Metamark MDiG

#### Performance Vinvl with MetaGlide® air release



### **Product Description**

Metamark MDiG features the MetaGlide® next generation air release system offering improved all round handling. With its micro structured air release liner, lift and reapply MetaGlide® graphics with a smooth clean peel that prevents damage to the graphic. MetaGlide® system offers exceptional layflat printability. Prints can stay stored or loosely rolled confidently without tunnelling or delamination. Metamark's 70 micron white face film with its distinctive coating technology produces outstanding print performance on Solvent, Eco Solvent, UV and Latex printers.

#### **Printing and Handling**

- Suitable for use on Solvent, Eco Solvent, Latex and U.V. inkjet printers. Always perform a test print first.
- Ensure that the correct profiles and heater settings are used. Most profiles are available for download from www.metamark.co.uk.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film directly and ensure it is free from dust and static.

#### **Overlaminating**

- Overlamination is recommended to prevent abrasion and to extend colour fastness.
- Allow the inks to cure before overlaminating, this is usually 24-48 hours.
- The matched laminate for MDiG is MetaGuard MGi. For all other laminates the user should determine suitability.

#### **Application**

- Allow the inks to cure before cutting flush to the print, this is usually 24-48 hours. Suitable for dry application only.
- Apply to flat surfaces or simple curves. Apply unstressed. Not suitable for application over rivets or into deep recesses.
- Not recommended for use on low energy surfaces such as polypropylene. The user should determine suitability of substrate.
- Refer to www.metamark.co.uk for application guidelines.

Face Film		Finishes			
Face Film: Gauge:	Polymeric Calendered PVC 70 micron nominal	Finishes Available	MDiG-100	White Gloss	
Tensile Strength	49N/25mm MD / 47N/25mm TD nom.	Roll Presentation			
Elongation at break	180% MD nominal	Dell siese	700		
Adhesive		Roll sizes	760mm x 25m / 50m 1370mm x 25m / 50m		
Municores			1600mm x 25m / 50m		
Туре	MetaGlide® Air Release Permanent	Presentation	Face film outwards, on a 76mm core.		
Weight	Solvent-Based Adhesive. 19gsm nominal	Durability			
Adhesion to glass 20 mins	10N/25mm nominal	Durubinty			
Adhesion to glass 24 hour	20N/25mm nominal	Shelf Life	2 years	5 years (International customers please	
Perceived tack	Medium	External weathering	, ,		
Application temperature Service temperature	+5°C to +60°C -30°C to +110°C		contact your local Metamark partner for confirmation of durability).		
oorvioo temperature	00 0 10 +110 0		This refers to the ur	-,	
Release Liner			to ink manufacturer for durability of the		
			finished product.		
Print	'MetaGlide®' purple print	Fire Rating	Class B. BS EN 13501-1:2007 <0.4mm (48h at 70°C on aluminium) The unprinted film is resistant to mineral oils, fats and fuels, aliphatic		
Weight	140 gsm nominal	Dimensional Stability Chemical Resistance			
Туре	Structured layflat kraft paper with PE coating	Glieffical Resistance			
	coating		solvents, mild acids		
			e.g. diesel oil, gasol	*	
			hydraulic oil, antifre	eze, soap suds, etc.	
		Regulations	REACH and RoHS compliant		
,					

Warranty: Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Digital Media will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark DigitalVinyl becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converteer is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. Please Note: The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

## Metamark (UK) Limited