

MetaGuard Decor

DécorMark Textured PVC Overlaminates



Product Description

The MetaGuard Decor range of textured overlaminates provide a highly durable protection over Metamark Digital films. These wall covering films give peace of mind and scuff resistance in high traffic areas. The attractive textured finish hides many imperfections on the wall, and enhances depth of colour to the print. The 150 micron polymeric films offer excellent dimensional stability.

Features and Benefits

- Matched to Metamark MD5 series.
- 150 micron textured film.
- Available in three finishes
- EN13501 fire certified.
- Textured anti-scuff finish.
- 7 year durability and MetaSure Warranty.

Face Film		Finishes		
Face Film	Polymeric Calendered PVC	Finishes Available	MG-W-002	SandTex
Gauge (ISO 2286-3)	150 micron nominal			
Tensile strength	65N/25mm MD / 57N/25mm TD norm			
Adhesive		Roll Presentation		
Type	Permanent clear pressure sensitive solvent-based acrylic with UV inhibitors	Roll Widths	0.76 / 1.37m / 1.52m	
Adhesion to glass 20 mins	15N/25mm nominal	Roll Lengths	25m	
Adhesion to glass 24 hour	20N/25mm nominal			
Application temperature	+10°C to +50°C	Durability		
Service temperature	-30°C to +100°C	Shelf Life	1 years. (10-20°C and 50% R.H).	
		Durability	7 years	
		Fire Rating	Class C - BS EN 13501-1:2007	
		Chemical Resistance	Unprinted film resistant to mild acids, aliphatic solvents, salt and alkali, diesel, gasoline, paraffin, hydraulic oil, antifreeze.	
Release Liner				
Print	'Metamark Digital Vinyl' grey print			
Weight	140 gsm nominal			
Type	Kraft paper with high internal strength and PE coating			

Handling and Application

- This product is suitable for cold lamination using a laminator.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film, ensure free from dust and static.
- Allow the inks to cure before overlaminating, this is usually 24-48 hours.
- Suitable for use on solvent, eco-solvent and latex prints.
- Apply around 30°C on the top roller to prevent silvering of the adhesive.
- Refer to www.metamark.co.uk for further application guidelines.
- The user should determine suitability of the overlaminate to the print media.

MetaSure® Warranty

Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Media and Overlaminates will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark Media and Overlaminates becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Metamark (UK) Limited

- Luneside • New Quay Road • Lancaster • LA1 5QP • Tel +44 (0)1524 387140
- Metamark House • Genesis Business Park • Albert Drive • Woking • GU21 5RW • Tel +44 (0)1483 571111

sales@metamark.co.uk
www.metamark.co.uk