MetaGuard 300

Intermediate Grade PVC Overlaminate



Product Description

MetaGuard 300 is recommended for Metamark MD3, and as a matched overlaminate prevents tunnelling or delamination. The 70 micron film gives a high level of abrasion resistance and contains UV stabilisers. It can be used on flat or gently curved surfaces such as vehicle graphics. Fire Rating Class B [BS EN 13501-1:2007]

Material Handling

- This product is suitable for cold lamination using a laminator.
- Ensure that the material has reached room temperature and a relative humidity of 50% before use.

Overlaminating

- Suitable for use on Solvent, Eco Solvent inkjet and Latex prints on Metamark print media. Not suitable for UV prints.
- The product is matched to Metamark MD3. The user should determine suitability of the overlaminate to other print media.
- Allow the inks to cure before overlaminating, usually 24-48 hours. Failure to do so can cause delamination, tunnelling and shrinkage.
- Apply around 30°C on the top roller to prevent silvering of the adhesive.
- Refer to www.metamark.co.uk for further application guidelines.
- The user should determine suitability of the overlaminate to the print media.

Face Film	
Face Film Gauge Tensile Strength Elongation at break	Calendered PVC 70 micron nominal 50N/25mm MD / 48N/25mm TD 180% MD nominal
Adhesive	
Type Weight Adhesion to glass 20 mins Adhesion to glass 24 hour Perceived tack Application temperature Service temperature	Permanent clear solvent-based acrylic with UV inhibitors 22gsm nominal 18N/25mm nominal 20N/25mm nominal Medium +5°C to +60°C -30°C to +110°C
Release Liner	
Print Weight Type	'Metamark Digital Vinyl' blue print 140 gsm nominal Kraft

Finisnes		
Finish Available	MG-302 MG-305	Matt Gloss
Roll Presentation		
Roll sizes and net weights	760mm x 50m 1370mm x 50m 1520mm x 50m 1600mm x 50m	
Presentation	Laminate outwards, o	n a 76mm core.
Durability		
Shelf Life External weathering	1 year 5 years. This refers to and not the protection printed image.	
Fire Rating	Class B - BS EN 13501 classification is 'B / s2	
Dimensional Stability Chemical Resistance	<0.4mm (48h at 70°C The unprinted film is r mineral oils, fats and f solvents, mild acids, s e.g. diesel oil, gasoline hydraulic oil, antifreeze	esistant to uels, aliphatic alt and alkali for e, paraffin,
Regulations	REACH and RoHS compliant	

Warranty: Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Digital Media will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark DigitalVinyl becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. Please Note: The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Metamark (UK) Limited