

SyntiSOL PP Film KissCut 325

— satin 3531 - 325 µm

SyntiSOL KissCut is a satin coated, adhesive and tear resistant polypropylene film with a water-resistant coating for solvent inks. This special "print and cut" film has a paper like touch and long durability . The low-tack glue grants easy application, as well as residue-free removal.

Applications

- High quality photo reproduction
- Indoor signs
- Indoor adverts
- Outdoor signage
- Billboard, outdoor advertising

Advantages

- High contrast and good image definition
- Quick dry
- High water-resistance
- Simple to stick, repositional and leaves no residue upon removal
- Outdoor application also possible
- Optimised for use on cutting plotters

SyntiSOL PP Film KissCut 325

— satin 3531 - 325 µm

List of Printers

Printer	Ink	Quality
Hewlett Packard DJ 8000S / 9000S / 10000S	Inkjet with Eco Solvent	Excellent
Epson Stylus Pro GS6000 UltraChrome GS	Inkjet with Eco Solvent	Excellent
Roland SolJet SJ540 / SC540 SJ 740 / SC740	Inkjet with Eco Solvent	Excellent
Roland VersaCAMM SP-300i / SP-540i	Inkjet with Eco Solvent	Excellent
Roland VersaCAMM VP-300i / VP-540i	Inkjet with Eco Solvent	Excellent
Roland VS 540 / VS 640	Inkjet with Eco Solvent	Excellent
Roland SolJET PRO4 XR-640	Inkjet with Solvent Ink	Excellent
Mimaki CJV 30	Inkjet with Eco Solvent	Excellent
Mimaki JV 33 / JV34 - 260	Inkjet with Eco Solvent	Excellent
Mimaki JV400SUV Serie	Inkjet mit Solvent-UV	Excellent
Océ CS9360 / CS935	Inkjet with Eco Solvent	Excellent
Epson SureColor SC-30600 / 50600 / 70600	Inkjet with Eco Solvent	Good
Mimaki JV-3 160S, 250	Inkjet with Solvent Ink	Good
Mimaki JV 5-130 / -160 / -260 /-320	Inkjet with Eco Solvent	Good
Mimaki CV300 Series Eco Solvent	Inkjet with Eco Solvent	Good
Mutoh Rockhopper 46", 62"	Inkjet with Eco Solvent	Good
Mutoh Rockhopper II 50", 64", 87"	Inkjet with Eco Solvent	Good

Last update: 18.02.2015

SyntiSOL PP Film KissCut 325**— satin 3531 - 325 µm****Physical Properties**

Weight (Total) [gsm]	280	ISO 536
Thickness (total) [microns]	325	ISO 534
Weight (without liner) [gsm]	145	ISO 536
Thickness (w/o release liner) [microns]	190	ISO 534
Opacity [%]	88	ISO 2471
Adhesion Strength Glas [N/25mm]	0,3	FTM 1 (24h)

Conditions of Use

The converting and storage should take place in a climate from 35 to 65% to relative humidity at a temperature from 10 to 30°C. Keep the product in the original packaging (cardboard box and PE bag). It is always recommended that cotton gloves be used when handling InkJet coated materials to avoid fingerprints.

[MediaSafetyDataSheet](#)

The values provided on this datasheet are only for orientation.

Before using our media please check its compatibility for your printer and intended application. Technical specifications are subject to change, therefore we do not take responsibility for any misprints resulting from technically modified inks and/or printers.